

CR-174652 VOLUME 2 OF 2 GARRETT 21-4314-2

(NASA-CR-174652) LOW-COST SINGLE-CRYSTAL TURBINE BLADES, VOLUME 2 (Garrett Turbine Engine Co.) 42 p HC A03/MF A01 CSCL 21E N86-23598

Unclas G3/07 06038

MATERIALS FOR ADVANCED TURBINE ENGINES

PROJECT COMPLETION REPORT PROJECT 3

LOW-COST, SINGLE-CRYSTAL TURBINE BLADES

VOLUME 2

by T.E. Strangman R.E. Dennis B.R. Heath

GARRETT TURBINE ENGINE COMPANY
A DIVISION OF THE GARRETT CORPORATION

APRIL 1984

Prepared for

National Aeronautics and Space Administration NASA-Lewis Research Center Contract NAS3-20073



FOREWORD

This Project Completion Report was prepared for the National Aeronautics and Space Administration, Lewis Research Center. It presents the results of a program conducted to establish exothermic heated casting technology for the manufacture of low-cost, single-crystal, uncooled turbine blades for gas turbine engines. The program was conducted as part of the Materials for Advanced Turbine Engines (MATE) Program under Contract NAS3-20073. This is Volume 2 of the Project Completion Report, covering the performance and endurance engine testing and post-test component analysis.

The authors wish to acknowledge the assistance and guidance of S. Grisaffe and R. L. Dreshfield of the NASA-Lewis Research Center in successfully completing this project.

PRECEDING PAGE BLANK NOT FILMED

TABLE OF CONTENTS

		Page
SECT	ION I	
1.0	SUMMARY	1
SECT	ION II	
2.0	INTRODUCTION	5
SECT	ION III	
3.0	FULL-SCALE ENGINE TESTING	7
	3.1 Performance Testing 3.2 Endurance Testing	10 17
SECT	ION IV	
4.0	POST-TEST EVALUATION	23
	4.1 Interim-Test Blade Evaluation 4.2 Post-Test Blade Evaluation	23 27
SECT	ION V	
5.0	CONCLUSIONS	35
SECT	ION VI	
6.0	RECOMMENDATIONS	37
REFI	RENCES	39

PRECEDING PAGE BLANK NOT FILMED

LIST OF ILLUSTRATIONS

Figure	<u>Title</u>	Page
1	Cycle A: First 50-Hour Test, High-Cycle- Fatigue Evaluation	8
2	Cycle B: Second 50-Hour Test, Stress Rupture Evaluation	8
3	Cycle C: Third 50-Hour Test, Simulated Commuter Jet Cycle	9
4	Cycle D: Fourth 50-Hour Test, Low-Cycle-Fatigue Evaluation	9
5	TFE731 Engine Installed in Phoenix Test Cell	12
6	MATE Rotor Assembly after Performance Testing, Showing Tip Rub	14
7	Tip View of MATE Rotor Assembly Following Performance Test	15
8	HP Turbine Shroud Following Performance Test of MATE SC Blades	16
9	Sketch Illustrating Flow Discourager Failure in Blade N27 During Second 50-Hour Test and Sketch Illustrating Flow Discourager Rework	18
10	Leading-Edge View of Typical Blades Subjected to the Entire 200 Hours of Endurance Testing	20
11	Trailing-Edge View of Typical Blades Subjected to the Entire 200 Hours of Endurance Testing	21
12	Visual Examination of SC NASAIR 100 Blade (S/N N27)	24
13	Extensive Interconnected and Oxidized Porosity and Incipient Melting Were Present in the NASAIR 100 Adjacent to the Failed Platform Web	25
14	Airfoil of Blade S/N N27 Exhibited a Microstructure Typical of Fully Processed SC NASAIR 100	26
15	Visual Appearance of SC NASAIR 100 (S/N N20, N33, N48) and SC Alloy 3 (S/N A42) Blades after the 200-Hour Engine Test	28

LIST OF ILLUSTRATIONS (CONTD)

<u>Figure</u>	<u>Title</u>	<u>Page</u>
16	Microstructure of SC Alloy 3 HP Turbine Blade (S/N A42) after 200-Hour Engine Test	29
17	Microstructure of SC NASAIR 100 HP Turbine Blade (S/N N48) after 200-Hour Engine Test	31
18	Scanning Electron Microscope Photographs (2000X) of SC NASAIR 100 HP Turbine Blade after 200-Hour Engine Test (S/N N48)	32
19	Appearance of the Blocky Alpha-Tungsten Phase in Airfoil Section of SC NASAIR 100 HP Turbine Blade	33
20	SEM Photograph and EDX Analysis of the Tungsten + Nickel Rich Mu Secondary Phase in the Airfoil Section of the SC NASAIR 100 Blade (S/N N48) after 200 Hours of Successful	
	Engine Testing	34

LIST OF TABLES

<u>Table</u>	<u>Title</u>	Page
1	Blade Substitution Plan for MATE Project 3 Engine Test	10

SECTION I

1.0 SUMMARY

The demand for more efficient and economical engines continues to push the industry toward higher turbine operating temperatures. The ability to maintain this trend is strongly tied to advancements in material technology. Single-crystal (SC) castings offer many significant advantages, such as higher melting point and higher strength, over turbine materials currently used in production engines. The goals of MATE Project 3 were to develop a low-cost casting process capable of producing SC turbine blades and to demonstrate the capability of the SC blades through extensive property, rig, and engine testing.

The following accomplishments are the most significant program goals achieved:

- o Incorporating the MATE high-pressure (HP) turbine blades and support hardware into the test engine reduced TSFC by 1.4 percent and T_5 (interturbine temperature) by 2.5 percent, compared to the baseline engine with uncooled directionally solidified (DS) HP turbine blades
- o The MATE single-crystal turbine blades, both NASAIR 100 and Alloy 3, successfully completed over 200 hours of endurance engine testing with no signs of distress
- o The exothermic casting process was successfully developed into a low-cost nonproprietary method for producing single-crystal castings.

Project 3 was divided into seven tasks. In Task I, the exothermic casting process was modified to consistently produce

acceptable solid SC high-pressure turbine blades for the TFE731 turbofan engine. This effort focused on the castability and base-line mechanical properties of blades produced with MAR-M 247.

During Task II, SC alloy derivatives of the MAR-M 247 alloy were assessed for castability, microstructure, and improvements in mechanical properties. Two of these SC compositions, NASAIR 100 and Alloy 3, were selected for detailed characterization.

In Task III, mechanical, environmental, and physical properties of SC NASAIR 100 and Alloy 3 were quantified. Mechanical property testing included creep rupture, tensile, and high—and low-cycle fatigue, and the determination of the effects of protective coatings. Environmental characterization included coated and uncoated oxidation and hot-corrosion tests. Physical properties measured included density, elastic modulus, thermal expansion, and thermal conductivity.

The SC HP turbine blade was designed in Task IV to utilize the improved mechanical properties of the prime SC alloy (NASAIR 100).

During Task V, two full sets of SC turbine blades and the required support hardware for both rig testing and the Task VI engine testing were manufactured. Rig and bench testing were also completed in Task V.

The results of the first five project tasks and the achievement of their related goals are presented in Volume 1 of the Project 3 Final Report (CR-168218, Garrett No. 21-4314-1). The results of the final two tasks--Task VI Engine Testing and Task VII Post-Test Evaluation--are presented in this document (Volume 2).

The Task VI Engine Testing was successfully completed. Testing consisted of back-to-back performance testing of a production configuration TFE731 engine with uncooled DS HP turbine blades and the same engine with the uncooled MATE SC HP turbine blades and related support hardware. This testing showed that the MATE engine configuration reduced TSFC by 1.4 percent and T_5 by 2.5 percent. Performance testing was followed by 200 hours of endurance engine testing, divided into the following four 50-hour segments:

- o 50-hours of high-cycle-fatigue (HCF) evaluation
- o 50 hours of maximum power (stress-rupture evaluation)
- o 50 hours of simulated commercial mission
- o 50 hours of low-cycle-fatigue (LCF) evaluation.

None of the blades subjected to the 200 hours of engine testing visually showed any detrimental effects from the testing. This was verified by the post-test metallurgical evaluation performed in Task VII.

SECTION II

2.0 INTRODUCTION

The NASA Materials for Advanced Turbine Engines (MATE) Program is a cooperative effort with industry to accelerate introduction of new materials into aircraft turbine engines. As part of this effort, Garrett Turbine Engine Company (GTEC) was authorized under NASA Contract NAS3-20073 to develop a new technique for manufacturing low-cost, single-crystal (SC), uncooled cast turbine blades to reduce SC casting costs and improve fuel consumption in advanced turbofan engines. The process development included those efforts required to transfer the technology from the previously demonstrated feasibility stage through component demonstration and engine test. Portions of the overall effort included process scale-up, alloy evaluations, mechanical property generation, hardware procurement, component testing, and full-scale engine testing to evaluate potential benefits.

This report constitutes Volume 2 of a two-volume Project Completion Report presenting the results of the investigations and tests performed under MATE Project 3, Low-Cost Single-Crystal Turbine Blades. This volume covers only the Project 3 full-scale engine testing and post-test analysis. All other aspects of this project are covered in Volume 1 of this report.

The intent of Project 3 was to develop a low-cost process to produce single-crystal, uncooled turbine blades and to design and substitute this blade for the solid, directionally solidified (DS) turbine blade used in the high-pressure turbine of the GTEC TFE731 turbofan engine.

Project goals associated with this program included the following:

PRECEDING PAGE BLANK NOT FILMED

- o Development of a nonproprietary, low-cost SC casting process
- o Improvement of the stress-rupture capability of the SC alloys relative to DS MAR-M 247
- o Design of an uncooled HP turbine blade to use the SC material
- o Demonstration of uncooled SC turbine blades through component and engine testing.

Project 3 was subdivided into the following seven tasks:

Task I - Casting Technology

Task II - Alloy/Process Selection

Task III - Property Characterization

Task IV - Blade Design

Task V - Component Manufacture and Testing

Task VI - Engine Testing

Task VII - Post-Test Evaluation

Tasks I through V are covered in detail in Volume 1 of this Project Completion Report. In this document, Volume 2, Task VI - Full-Scale Engine Testing and Task VII - Post-Test Evaluation are covered in detail, including recommendations concerning the future of the exothermic SC casting process and SC HP turbine blades.

The results of Tasks VI and VII--project completion information-are restricted by the NASA For Early Domestic Dissemination (FEDD) policy. The FEDD legend, describing the requirements of this policy, is printed on the cover of this document.

SECTION III

3.0 FULL-SCALE ENGINE TESTING

Scope

The objectives of the Task VI Engine Testing were as follows:

- (1) Verify the anticipated reduction in TSFC with the SC turbine blades
- (2) Demonstrate the durability of both the material and the design of the new blade. The program required that the HP blades produced in Task V be subjected to 200 hours of typical engine operating conditions in an appropriate GTEC engine.

The Task VI Engine Testing of the fully processed HP turbine blades consisted of back-to-back performance tests followed by four 50-hour endurance test segments chosen by GTEC and approved by The performance test was designed to compare a production DS turbine configuration with the same engine using the MATE Project 3 SC turbine blades. The four 50-hour test segments, in the order performed, were designed to evaluate the resistance of the SC blade to high-cycle fatigue, stress-rupture, a simulated commercial mission, and low-cycle fatigue. These test conditions were chosen to allow direct comparison of the SC blades produced in this project with the production DS uncooled (solid), MAR-M 247 turbine blades. The test cycles for these four test segments are shown in Figures 1, 2, 3, and 4. The blade substitution schedule presented in Table 1 was used to expose groups of test blades to single and multiple loading conditions established by the test parameters of the four This substitution plan permitted comprehensive 50-hour tests. post-test evaluation of the individual and combined effects of the four test segments by both nondestructive and destructive techniques.




Figure 1. Cycle A: First 50-Hour Test, High-Cycle-Fatigue Evaluation.




Figure 2. Cycle B: Second 50-Hour Test, Stress-Rupture Evaluation.




Figure 3. Cycle C: Third 50-Hour Test, Simulated Commuter Aircraft Mission.




Figure 4. Cycle D: Fourth 50-Hour Test, Low-Cycle-Fatigue Evaluation.

TABLE 1. BLADE SUBSTITUTION PLAN FOR MATE PROJECT 3 ENGINE TEST.

		Number of Blades Substituted for Each Test Cycle										
Material	A	В	С	D	A+B	B+C	C+D	A+D	A+B+C	B+C+D	A+B+C+D	Totals
NASAIR 100		2	2	2	2	2	1	4	1	1	18	35
Alloy 3	2						1		1	1	34	39
Totals	2	2	2	2*	2	2	2*	4*	2	2*	52*	74

A = 50-Hour High-Cycle-Fatigue Evaluation (Figure 1)

B = 50-Hour Stress-Rupture Evaluation (Figure 2)

C = 50-Hour Simulated Mission Evaluation (Figure 3)

D = 50-Hour Low-Cycle-Fatigue Evaluation (Figure 4)

*Blades in engine at end of 200-hours

3.1 Performance Testing

The MATE Project 3 SC HP turbine blade is essentially the same configuration as the production DS turbine blade, except for the addition of a tip winglet and an aft platform flow discourager. To accommodate this new blade design, minor modifications were made to some of the surrounding hardware.

To use the superior temperature capability of the SC materials, cooling air supplied to the fore and aft sides of the HP turbine disk was reduced by blocking part of the cooling air entry holes. Seals were added between the blades to prevent cooling air from leaking out and hot gas from being ingested between the blade platforms, and the firtree seal was eliminated to allow more cooling airflow through the firtree. The net effect of these modifications was to reduce the cooling airflow while maintaining adequate cooling air to the disk and blade firtree.

Back-to-back performance tests were conducted to evaluate the effect of the SC blade and support hardware on the measured engine performance. Testing was done in a fan test cell located in GTEC's Phoenix facility, with standard instrumentation. Figure 5 shows the TFE731 installed in the fan test cell.

Following the standard production engine performance baseline test, the engine was rebuilt to the MATE Project 3 configuration, substituting the following hardware for the original production hardware.

PART NAME

MATE HPT Blades - NASAIR 100
MATE HPT Blades - Alloy 3
ITT Duct
HPT Shroud Segments
LPT Nozzle Duct
Shroud Retaining Sleeve
Aft Curvic Coupling
HPT Seal Plate
HPT Nozzle, 26 Vane




Figure 5. TFE731 Engine Installed in Phoenix Test Cell.

The engine with this new hardware was then run through the standard performance calibration, using the same test cell and instrumentation that was used for the baseline performance test.

Reduction of the performance data to standard-day conditions indicated the following:

- O The baseline standard engine was well within production test limits.
- o Incorporating the MATE Project 3 SC turbine blades and support hardware into the same engine produced a measured 1.4 percent reduction in TSFC and reduced T₅ by 2.5 percent.

These performance improvements are directly related to the increased efficiency of the MATE HP turbine blade and the decrease in cooling flow.

Upon disassembly of the engine, a slight rub was found at approximately the 2 o'clock position, forward looking aft. Figures 6, 7, and 8 show that the assembly and shroud interference was minor.

Visual and fluorescent penetrant inspection (FPI) was completed after teardown, with no distressed parts identified. Several new blades were substituted for endurance testing, and the wheel was reassembled and balanced for the first endurance test. To avoid further rubs, the ID of the stator shrouds were resized to the maximum diameter allowed for production engines.




Figure 6. MATE Rotor Assembly After Performance Testing.



Figure 7. Tip View of MATE Rotor Assembly Following Performance Test.




Figure 8. HP Turbine Shroud Following Performance Test of MATE SC Blades.

3.2 Endurance Testing

Endurance testing was accomplished in four 50-hour test segments with a teardown inspection after each 50-hour test. Figures 1, 2, 3, and 4 (previously shown) represent the four test cycles used during endurance testing. The blade substitution schedule presented in Table 1 was used to expose test blades to various combinations of single and multiple loading conditions to isolate the effects of the various tests on the blades.

All endurance testing was done with standard engine monitoring instrumentation at GTEC's remote test facility located at San Tan, Arizona.

The first 50-hour test cycle was established to verify the MATE Project 3 blade response and evaluate the resistance to high-cycle fatigue (Figure 1). This test was accomplished as scheduled. No operating problems occurred during this test, and all test parameters were within limits. Post-test inspection revealed no distress on any of the SC blades or support hardware. Blades were substituted into the rotor assembly in accordance with the previously established substitution plan, the rotor was rebalanced, and the engine was reassembled for the second 50-hour endurance test.


The stress-rupture endurance test cycle used for the second test was shown previously in Figure 2. Again, no problems were encountered during testing. However, post-test inspection revealed that one blade (S/N N27) had lost approximately fifty percent of the aft flow discourager. Figure 9A is a sketch of the failed blade. No other signs of distress were found on the remaining SC blades, but moderate foreign object damage (FOD) was found on the first and second LP turbine stages.

Detailed examination of the failed blade indicated that the flow discourager web thickness was undersized and contained excessive porosity due to microshrinkage. Preliminary conclusions were that the platform, undersized and weakened by excessive casting porosity, could not carry the centrifugal bending load and failed

at the thinnest section. Further details of this blade examination and analysis confirmed the preliminary conclusion and are reported in the post-test-evaluation section of this report.

In addition to the visual and FPI inspections scheduled between endurance tests, the web thickness of each blade was measured and the casting porosity in each web was carefully evaluated. Three blades were eliminated from further testing due to the combination of a thin platform web and excessive porosity.

To avoid any chance of additional platform failures, all remaining blades were reworked (as shown in Figure 9B) to reduce the






Figure 9A. Sketch Illustrating Flow Discourager Failure in Blade N27 During Second 50-Hour Test.

Figure 9B. Sketch Illustrating Flow Discourager Rework.

stress in the flow discourager region. The reworked blades were then reassembled into the disk with blades substituted according to the schedule. The rotor was rebalanced, the damaged LP turbine components replaced, and the engine reassembled for the third 50-hour endurance test.

The third 50-hour test cycle simulated a typical mission for a commuter aircraft (Figure 3). No problems were encountered during this test, and no significant changes in operating parameters were observed as a result of the blade rework. Post-test inspection found no signs of distress in the blades or any other component. Blade substitutions were again made according to the schedule, the wheel rebalanced, and the engine reassembled for the fourth and final 50-hour test.

The fourth 50-hour test cycle, designed to provide an evaluation of the low-cycle-fatigue capability of the SC blades, is shown in Figure 4. Normal accelerations and decelerations were maintained for all cycles. No significant engine test problems were encountered during this test, and engine performance remained consistent with previous testing. The post-test inspection did not reveal any discrepancies in the SC blades or any other hardware. Figures 10 and 11 show typical leading and trailing edge views of blades tested for the entire 200 hours.

Detailed examinations of sample test blades were accomplished according to the scheduled evaluation. Results of these inspections are presented in the post-test evaluation section of this report.




Figure 10. Leading-Edge View of Typical Blades Subjected to the Entire 200 Hours of Endurance Testing.




Figure 11. Trailing-Edge View of Typical Blades Subjected to the Entire 200 Hours of Endurance Testing.

4.0 POST-TEST EVALUATION

4.1 <u>Interim-Test Blade Evaluation</u>

After 100 hours of testing (Cycles A and B), routine examination of the HP turbine rotor indicated that one of the SC NASAIR 100 blades (S/N N27) had lost part of the aft flow discourager. The weight of the missing piece was estimated at about one gram. To identify the cause of this flow discourager failure and to document the microstructure of the airfoil, this blade was visually and metallurgically examined. These examinations (Figures 12 and 13) revealed that the flow discourager web thickness was significantly below the minimum specified drawing thickness and only about 65 percent of the average web thickness. The portion of the platform web that failed also had very high amounts of oxidized (surface connected) porosity.

FPI and visual inspection of the remaining blades indicated that comparable platform porosity was present in many of the blades. However, no other blades had the excessive platform porosity and below minimum web thickness that combined to produce a failure.

Microstructural analysis of blade S/N N27 at other locations on the blade was also performed (Figures 13 and 14). This analysis indicated that the SC NASAIR 100 blade had been solution heattreated at the upper end of the solution heat-treatment window. The eutectic gamma prime phase was completely solutioned and minor incipient melting was observed in the blade root. Substantially less microporosity was noted in the airfoil than in the blade root. Energy dispersive X-ray (EDX) analysis was used to verify the NASAIR 100 composition of blade S/N N27.





Figure 12. Visual Examination of SC NASAIR 100 Blade (S/N N27)
Confirms that Substantial Porosity and a Very
Thin Platform Web Contributed to an Overload
Fracture of the Flow Discourager Tooth During
the Second 50-Hour (Maximum Continuous Power)
Segment of the Engine Test. (Photographs are
75 percent of indicated magnifications.)

MP-87775

INTERCONNECTED POROSITY



INCIPIENT MELTING

Figure 13. Extensive Interconnected and Oxidized Porosity (top) and Incipient Melting (bottom) Were Present in the NASAIR 100 Adjacent to the Failed Platform Web (SC NASAIR 100 Blade S/N N27). Photographs are 85 percent of indicated magnifications.

1




Figure 14. Airfoil of Blade S/N N27 Exhibited a
Microstructure Typical of Fully Processed
SC NASAIR 100. (Photographs are 80 percent
of indicated magnifications.)

4.2 Post-Test Blade Evaluation

Following the removal of the flow discourager tooth edge from the remaining SC blades (described previously in this report), the last two test cycles (C and D) were completed without incident. At the completion of the required 200 hours of testing, all NASAIR 100 and Alloy 3 turbine blades were carefully examined by both FPI and visual inspection at magnifications up to 40%. No evidence of distress was noted on any of the blades.

In addition to the FPI and visual inspections, three SC NASAIR 100 blades (S/N N20, N33, and N48) and one SC Alloy 3 blade (S/N A42), which had been exposed to the full 200 hours of the engine test, were selected for metallographic examination. The appearance of the blades at the conclusion of the test and the location of the longitudinal metallographic section are provided in Figure 15.

Results of the examination of the SC Alloy 3 blade S/N A42 are provided in Figure 16. Metallographic examination indicated that the single-crystal alloy was fully solutioned with no evidence of incipient melting. Minimal porosity was observed in the airfoil, with higher amounts present in the blade root. Scanning electron microscopy (SEM) indicated that the cubic gamma prime precipitate morphology was retained in the blade root and the minimally stressed tip region of the airfoil. In contrast, the cubic gamma prime phase transformed to platelets aligned perpendicular to the applied centrifugal stress in the [001] direction in the higher temperature portion of the airfoil. Data in the literature indicates that this gamma prime morphology, commonly known as rafting, occurs at low creep strains and reduces subsequent creep rates. 2,3 Rafting of the gamma prime phase in the airfoil was the only metallurgical modification associated with operation in this engine.

Post-test metallographic analysis of the SC NASAIR 100 blades indicated that they had been solution heat-treated at the upper limit of the heat-treatment window. The eutectic gamma prime had




Figure 15. Visual Appearance of SC NASAIR 100 (S/N N20, N33, N48) and SC Alloy 3 (S/N A42) Blades after the 200-Hour Engine Test. Vertical Lines Indicate Location of Longitudinal Metallographic Section.

MP-87838




Figure 16. Microstructure of SC Alloy 3 HP Turbine Blade (S/N A42) after 200-Hour Engine Test.

been completely solutioned, and some indications of incipient melting were observed in the three blades examined. Results of the microstructural examination of Blade S/N N48 illustrate this condition (Figure 17). In some instances, the amount of incipient melting slightly exceeded the one-volume percent permitted by the SC NASAIR 100 specification (see Volume 1). This condition, however, did not affect the performance of the blades in the engine test.

SEM examination of the SC NASAIR 100 blades indicated that the gamma prime phase had undergone modifications similar to the SC Alloy 3 material. As shown in Figure 18, the gamma prime phase had rafted in the central region of the airfoil. The morphology of the rafted gamma prime phase is similar to that reported by Nathal and Ebert³ for NASAIR 100 at the initiation of secondary (steady-state) creep. The cubic gamma prime phase morphology, which is typical of a fully processed casting, was retained in the relatively cool blade root and in the lightly stressed, but hotter, airfoil location near the blade tip.

Two types of minor secondary phases were also observed in the SC NASAIR 100 turbine blades. A blocky alpha-tungsten phase, which is present in as-cast blades, was observed throughout the root, airfoil, and tip (Figures 17 and 18). This phase is shown in a high magnification SEM photograph in Figure 19. As expected, the nickel-tungsten-rich Mu phase was also observed in the hotter airfoil sections of the SC NASAIR 100 blades after the 200-hour engine exposure (Figure 20). The Mu phase was most commonly observed in the airfoil section, where the rafted gamma prime phase was well developed (see Figures 18, 20).

It should be noted that extensive long-term testing of SC NASAIR 100 specimens (see Volume 1) indicated that the Mu phase, in the amounts observed, was innocuous. Consistent with this information, the Mu phase did not adversely affect the integrity of the SC NASAIR 100 HP turbine blades during the 200-hour engine test.





Figure 17. Microstructure of SC NASAIR 100 HP Turbine Blade (S/N N48) after 200-Hour Engine Test.



MA16568

Figure 18. Scanning Electron Microscope Photographs (2000X) of SC NASAIR 100 HP Turbine Blade after 200-Hour Engine Test (S/N N48).




Figure 19. Appearance of the Blocky Alpha-Tungsten Phase (Arrows) in Airfoil Section of SC NASAIR 100 HP Turbine Blade.




Figure 20. SEM Photograph and EDX Analysis of the Tungsten+ Nickel Rich Mu Secondary Phase in the Airfoil Section of an SC NASAIR 100 Blade (S/N N48) after 200 Hours of Successful Engine Testing.

SECTION V

5.0 CONCLUSIONS

The following conclusions were based upon the results of the engine testing and post-test analysis of the SC turbine blades presented in this report:

- o Incorporating the MATE HP turbine blades and support hardware into the test engine reduced TSFC by 1.4 percent and T_5 by 2.5 percent compared to a baseline engine with directionally solidified HP turbine blades.
- o The MATE single-crystal turbine blades, both NASAIR 100 and Alloy 3, showed no signs of distress after successfully completing over 200 hours of endurance engine testing.

SECTION VI

6.0 RECOMMENDATIONS

After completion of the engine testing and the post-test evaluation of the SC turbine blades, the following recommendations can be made:

- o Blade Design The SC blade performed well in the engine test, both from efficiency and durability standpoints. The only change recommended is a review of the aft flow discourager design. Better thickness control or a change in thickness is required if the tolerances between the cast outer surface or the machined inner surface cannot be reduced.
- o Process Control Plan Due to the changes in the investment casting industry since this project was initiated,
 it is recommended not to pursue further development of
 the exothermic SC process. The major casting houses have
 already made the capital investment in withdrawal equipment, thus eliminating one advantage of the exothermic
 process. Therefore, unless the proprietary aspect of the
 SC withdrawal process becomes a significant problem, further development of the exothermic process is not recommended.
- o Property Specifications and Blade Acceptance Criteria No changes are recommended in either of these items at
 this time. However, these areas are constantly reviewed
 and compared to engine test experience. Thus, changes in
 either or both may be desired as the GTEC experience base
 grows.

PRECEDING PAGE BLANK NOT FILMED

REFERENCES

- Strangman, T.E., B.R. Heath, and M. Fujii: Low-Cost, Single-Crystal Turbine Blades Volume 1, Garrett Report No. 21-4314-1, NASA CR-168218, 1983.
- 2. Pearson, D.D., F.D. Lemkey and B.H. Kear: "Stress Coarsening of γ' and its Influence on Creep Properties of a Single-Crystal Superalloy," in Superalloys 1980 Proceedings of the Fourth International Symposium on Superalloys, Champion, Pennsylvania, September 1980, pp. 513-520.
- 3. Nathal, M.V. and L.J. Ebert, "Gamma Prime Shape Changes During Creep of a Nickel-Base Superalloy," Scripta Metallurgica, 17 (1983), 1151-1154.

PRECEDING PAGE BLANK NOT FILMED

DISTRIBUTION LIST

NASA Headquarters Attn RTM-6/M. Greenfield 600 Independence Ave., SW Washington, DC 20546

NASA Headquarters Attn RT-6/R. Colladay 600 Independence Ave., SW Washington, DC 20546

NASA Lewis Research Center Attn C. M. Scheuermann MS 105-1 21000 Brookpark Road Cleveland, OH 44135 NASA Lewis Research Center Attn H.B. Probst, MS 49-3 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn H.R. Gray, MS 49-3 R. V. Miner 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn C.E. Lowell MS49-1 21000 Brookpark Rd. Cleveland, OH 44135

NASA Lewis Research Center Attn R.A. Rudey, MS 60-4 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn: A. Powers MS 500-127 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn L. Hibbin 500-211 21000 Brookpark Road Cleveland, OH 44135 NASA Lewis Research Center Attn Section 1411-DT MS 501-11 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn AFSC Liason Office MS 501-3 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn US Army Propulsion Lab. MS 302-2 Cleveland, OH 44135

NASA Lewis Research Center Attn R.L. Dreshfield MS 105-1 21000 Brookpark Road Cleveland, OH 44135 (10 copies) NASA Lewis Research Center Attn R. L. Davies MS 105-1 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn L. Berke, MS 49-6 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn S.J. Grisaffe MS 49-1 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn S. Levine MS 105-1 21000 Brookpark Rd Cleveland, OH 44135 NASA Lewis Research Center Attn R.A. Signorelli MS 106-1 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn K. Sievers MS 501-7 21000 Brookpark Road Cleveland, OH 44135 NASA Lewis Research Center Attn R.C. Bill 49-6 21000 Brookpark Road Cleveland, OH 44135

NASA Lewis Research Center Attn Tech Utilization MS 3-19 21000 Brookpark Road Cleveland, OH 44135 NASA Lewis Research Center Attn Library, MS 60-3 21000 Brookpark Road Cleveland, OH 44135 (2 copies)

NASA Lewis Research Center Attn Report Control MS 5-5 21000 Brookpark Road Cleveland, OH 44135 NASA Ames Research Center Attn N. Kurkowski 210-10 Moffett Field CA 94035

NASA Ames Research Center Attn Library Moffett Field CA 94035 NASA Langley Rsch Center Attn Library Langley Field, VA 23365

NASA MSFC Attn W. B. McPherson EH23 Huntsville AL 35812 NASA MSFC Attn Library Huntsville AL 35812

U.S.Air Force Attn AFAPL/TBC L. Gill Wright-Patterson AFB OH 45433 U.S. Air Force Attn AFWAL/MLLM W. Reimann Wright Patterson AFB OH 45433

U.S. Air Force Attn AFAPL/CCN Chief Scientist Wright Patterson AFB OH 45433 U.S. Air Force Attn AFML/LTM H. Johnson Wright-Patterson AFB OH 45433

U.S. Air Force Attn AFML/LTM J.K. Elbaum Wright-Patterson AFB OH 45433

U.S. Air Force Attn AFML/LLM R. M. Dunco Wright-Patterson AFB OH 45433

U.S. Air Force Attn E. A. Lake Wright-Patterson AFB OH 45433

U.S. Air Force Attn AFWAL S. Fujishiro Wright-Patterson AFB OH 45433

Eustis Directorate
Applied Tech Lab
Army Rsch and Tech Lab
Attn J. Lane AVRADCOM
Fort Eustis, VA 23604

Army Materials & Mechanics Research Center Attn S. Isserow DRXMR-KA P. Smoot Watertown, MA 02172

NASA MSFC Attn L. Scarborough Code EP-24 Huntsville AL 35812 NASA MSFC Attn R. Schwinghammer Huntsville AL 35812

U.S. Air Force Attn AFML/LLM N. Geyer Wright-Patterson AFB OH 45433 U. S. Air Force Attn Lt. Col. D. Quick AFWAL/POTC Wright Patterson AFB OH 45433

U.S. Air Force Attn AFWAL/POTC R. Henderson Wright-Patterson AFB OH 45433 U.S. Air Force
Attn AFAPL/TBP P. Copp
T. Fecke
Wright-Patterson AFB
OH 45433

U.S. Air Force Attn AFWAL/NASA-PO E. Bailey Wright Patterson AFB OH 45433

U.S. Air Force Attn AFAPL/TBC C.W. Elrod Wright Patterson AFB OH 45433

U.S. Air Force Attn AFML/LLM W. O'Hara Wright-Patterson AFB OH 45433

U.S. Air Force Attn AFML/LAM Library Wright-Patterson AFB OH 45433

U. S. Air Force Attn A. Rosenstein AFOSR/NE-Bldg. 410 Bolling Air Force Base Washington, DG 20332

Army Materials & Mechanics Research Center Attn F. Hodi DRXMR-EM Watertown, MA 02172

Army Materials & Mechanics Research Center Attn J.W. McCauley Watertown, MA 02172

Navy Department Naval Air Systems Command Attn J. Collins Air-5304 B Washington, D.C. 20361

Office of Naval Research Attn B. MacDonald Code 471 800 N. Quincy St Arlington, VA 22217

Navy Department Attn L. F. Aprigliano Code 2812 Annapolis, MD 21402

FAA Headquarters
Attn T.G. Horeff
800 Independence Ave., SW
Washington, DC 20591

AVCO Lycoming Div. Attn A. DeFerrari 550 S. Main St. Stratford, CT 06497 NASA STIF Attn Accessioning Dep't P.O. Box 8757 Balt-Wash Int'hat Airport Maryland 21240 (20 copies)

Army Materials & Mechanics Research Center Attn P. Ahearn Watertown, MA 02172

Army Materials & Mechanics Research Center Attn Library Watertown, MA 02172

Navy Department
Haval Air Systems Command
Attn. C. Miller
Air 5143C JP2
Washington, D.C. 20361

Research & Technology Div. NAPTC Attn J. Glatz Trenton, NJ 08628

DOE Attn S. Dapkunas 4203 20 Massachusetts Ave Washington, D.C. 20545

FAA Headquarters
Attn N. P. Krull AEQ-10
800 Independence Ave., SW
Washington, DC 20591

AVCO Lycoming Div. Attn P. Banla 550 S. Main St. Stratford, CT 06497

Curtiss-Wright Corp.
Attn E. Troc
1 Passaic St
Wood Ridge, NJ 07075

Detroit Diesel Allison Attn G.L. Vonnegut W-13 2001 S. Tibbs Ave Indianapolis, IN 46206

Defense Advanced Research Projects Agency ARPA/SMO Attn. E. C. Van Reuth 1400 Wilson Blvd. Arlington, VA 22209 Inst. for Defense Analysis Attn J. Hove 400 Army Navy Drive Arlington VA 22202

Navy Department
Naval Air Systems Command
Attn J.L. Byers
Air-5360C
Washington, D.C. 20361

Naval Air Dev. Center Attn M.K. Thomas (60631) Warminster, PA 18974

Naval Sea System Attn S.B. Shepard 5231 Washington, DC 20362 Navy Department Attn G. A. Wacker, Head Met. Div., Code 281 Naval Ship R&D Center Annapolis, MD 21402

FAA Headquarters Attn R. Berman AWS-141 800 Indendence Ave Washington, DC 20951 FAA Headquarters Attn A. Broderick AEQ 10 800 Independence Ave., SW Washington, DC 20591

AVCO Lycoming Div. Attn J. Walters 550 S. Main St. Stratford, CT 06497 AVCO Lycoming Div. 'Attn L.J. Fiedler 550 S. Main St. Stratford, CT 06497

Curtiss-Wright Corp. Attn J. Mogul 1 Passaic St Wood Ridge NJ 07075 Curtiss-Wright Corp. Attn R. Yellin 1 Passaic St Wood Ridge ,NJ 07075

Detroit Diesel Allison Attn B.A. Ewing P.O. Box 894 T-27 Indianapolis, IN 46206 Detroit Diesel Allison Attn M. Doner P.O. Box 894 W5 Indianapolis, IN 46206

Detroit Diesel Allison Attn J. Byrd s/c U24 P.O. Box 894 Indianapolis, IN 46206 Detroit Diesel Allison Attn M. Herman P.O. Box 894 Indianapolis, IN 46206

General Electric Co. Attn C. Sims, Bldg 53 Gas Turb Prod. Div. Schenectady, NY 12345 General Electric Co. Attn L. Peterson Gas Turbine Prod. Div. 1 River Rd. Schenectady, NY 12345

General Electric Co.
Material and Processing
Attn E. Kerzicnik M82
Evandale, OH 45215

General Electric Co.
Materials and Processing
Attn R. Sprague M82
Evandale, OH 45215

General Electric Co.
Material and Processing
Technology Laboratory
Attn J. Erickson M82
Evandale, OH 45215

General Electric Company Attn Tech Info Cntr N-32 Evandale, OH 45215

General Electric Co.
Attn G. Deboer
Material and Processing
Technology Laboratory
Evandale, OH 45215

General Electric Co. Attn W. E. Kurz Mgr. MDO 1000 Western Ave. Lynn, MA 01910

General Electric Co.
Corporate R+D Center
Attn M. Benz
P. O. Box 8
Schenectady, NY 12301

General Electric Co.
Corporate R+D Centet
Attn M.F.X. Gigliotti
P. O. Box 8
Schenectady, NY 12301

Pratt and Whitney Aircraft Commercial Products Attn A. Hauser 400 Main St. East Hartford, CT 06108 Pratt and Whitney Aircraft Commercial Products Attn M. Gell 400 Main St. East Hartford, CT 06108

Detroit Diesel Allison Attn N. Provenzano U29A P.O. Box 894 Indianapolis, IN 46206 Detroit Diesel Allison Attn J. Lyon P.O. Box 894 Indianapolis, IN 46206

General Electric Co. Attn F. D. Lordi, Bldg 53 Gas Turb Prod. Div. Schenectady, NY 12345 General Electric Co. Attn W. Schilling Bldg 53 Gas Turb Prod. Div. Schenectady, NY 12345

General Electric Co. Material and Processing Technology Attn T. F. Berry Evandale, OH 45215 General Electric Co. Material and Processing Technology Laboratory Attn L. Wilbers M87 Evandale, OH 45215

General Electric Co. Material and Processing Technology Laboratory Attn N. Fairbanks Evandale, OH 45215 General Electric Co. Material and Processing Technology Laboratory Attn R. E. Allen Evandale, OH 45215

General Electric Co. Attn J. Hsia AEG/GED 1000 Western Ave. Lynn, MA 01910 General Electric Co. Attn G. Steele Irons Mgr. Casting Tech. 1000 Western Ave. Lynn, MÅ 01910

General Electric Co.
Corporate R+D Center
Attn Library
P. O. Box 8
Schenectady, NY 12301

Pratt and Whitney Aircraft Commercial Products Attn S. Blecherman Aircraft Road Bldg 140 Middletown CT 06457

Pratt and Whitney Aircraft Commercial Products Attn C. P. Sullivan 400 Main St. East Hartford, CT 06108 Pratt and Whitney Aircraft Manufacturing Div. Attn J. Zubeckis 400 Main St. East Hartford, CT 06108

Pratt and Whitney Aircraft Manufacturing Div. Attn F. M. Heinrich 400 Main St. East Hartford, CT 06040 Pratt and Whitney Aircraft Attn J. Moore Box 2691 West Palm Beach FL 33402

Pratt and Whitney Aircraft Attn H. Przirembel Box 2691 West Palm Beach FL 33402 Solar Attn A. Stetson P.O. Box 80966 San Diego, CA 92138

Williams Research Attn Wm. P. Schimmel 2280 W. Maple Walled Lake, MI 48088 Williams Research Attn Library 2280 W. Maple Walled Lake, MI 48088

Williams Research Attn J. Carlton 2280 W. Maple Walled Lake, MI 48088 Airco Temescal Attn L. Bianchi 2850 Seventh St. Berkeley, CA 94710

Battelle Memorial Inst Attn D. Niesz 505 King Ave. Columbus, OH 43201

Battelle Memorial Inst Attn Technical Library 505 King Ave. Columbus, OH 43201

The Boeing Co Attn H. D. Kevin 41-SH P.O. Box 3999 Seattle, WA 98124 Boeing - Wichita Div. Attn Wm. F. Schmidt org. 75930 Propulsion Wichita, KS 67210

Cameron Iron Works Attn Library P. O. Box 1212 Houston, TX 77001

Cannon-Muskegon Corp. Attn G. L. Erickson P.O. Box 506 Muskegon, MI 49443

Pratt and Whitney Aircraft Attn H. L. Hess, Jr Box 2691 West Palm Beach FL 33402 Pratt and Whitney Aircraft Attn J. Winfree Box 2691 West Palm Beach FL 33402

Solar Attn A. Metcalfe P.O. Box 80966 San Diego, CA 92138

Teledyne CAE
Mat. Dev. and Manuf. Engr
Attn R. Beck
PO Box 6971
Toledo, OH 43612

Williams Research Attn J. Jones 2280 W. Maple Walled Lake, MI 48088 Williams Research Attn P. Nagy 2280 W. Maple, Walled Lake, MI 48088

Airco Temescal Attn W.K. Halnan 2850 Seventh St. Berkeley, CA 94710 Battelle Memorial Inst Attn K. Meiners 505 King Ave. Columbus, OH 43201

Beech Aircraft Corporation Attn C A. Rembleske 9709 E. Central Ave. Wichita, KS 67201 Boeing Comm. Airplane Co Attn W. Blissell 9H-43 P.O. Box 3707 Seattle, WA 98124

Brown Boveri Turbo. Inc. Attn A. Giammarise L. Engel 711 Anderson Ave. N St. Cloud, MN 56301 Brunswick Corp. Attn. R. Tolokan 2000 Brunswick Lane Deland, FL 32720

Cannon-Muskegon Corp. Attn R. Quigg P.O. Box 506 Muskegon, MI 49443 Carpenter Technology Corp. Attn G. DelCorso A. Walsh R/D Lab, Bldg. 68 Reading, PA 19603

Cartech Inc. Attn E. Berger P.O. Box 662 Reading, PA 19603 Cessna Aircraft Co. Attn A. Kavie (Turbofan) Wallace Division P.O. Box 7704 Wichita, KS 67277

Chrysler Corp.
Attn F.A. Hagen
Box 1118 CIMS 418-19-30
Detroit, MI 48288

Climax Molybdenum Co. Attn Wm. Hagel P.O. Box 1568 Ann Arbor, MI 48106

DCI Inc. Attn R. Engdahl 318 Victory Drive Herndon, VA 22070 Defense Marketing Services Attn D. Franus 100 Northfield St. Greenwich, CT 06830

Duradyne Tech. Inc. Attn R. Horton 8607 Tyler Blvd Mentor OH 44060 Engelhard Industries Attn E. Grider Route 152 Plainville, MA 02762

Gates Learjet Corp.
Attn W. J. Reese
C. L. King
P.O. Box 7707
Wichita KS 67277

Gates Learjet Corp. Attn T. Reichenberger P.O. Box 7707 Wichita, KS 67277

General Motors Corp. Attn A. Bell Advanced Prod Engr Technical Center Warren, MI 48090

General Motors Corp. Attn K. Bly 73-S Technical Center Warren, MI 48090

Grumman Aerospace Corp. Attn C. Hoelzer C32-5 Bethpage, NY 11714 Howmet Turbine Comp. Div. Attn W. Freeman 475 Steamboat Road Greenwich, CT 06830

Cessna Aircraft Co. Attn C. Gonzales (Turboprop) Wallace Division P.O. Box 7704 Wichita, KS 67277 Chromoloy Attn D. Kenton P.O. Box 10699 Midwest City, OK 73140

Colt Industries
Attn E. Dulis
Crucible Inc, Mat'ls Rsch
P. O. Box 88
Pittsburgh, PA 15230

Colt Industries
Attn J. Moll
Crucible Inc, Mat'ls Rsch
P. O. Box 88
Pittsburgh, PÅ 15230

Delta Airlines Attn W.J. Overend Atlanta Airport Atlanta, GA 30320 Douglas Aircraft Co. Attn Library McDonnell Douglas Corp 3855 Lakewood Blvd. Long Beach, CA 90846

Ford Motor Company Attn C. Feltner Metallurgical Dept. P.O. Box 2053 Dearborn, MI 48121

Ford Motor Company Attn Y. Telang Metallurgical Dept. P.O. Box 2053 Dearborn, MI 48121

Gates Learjet Corp. Attn A. M. Heinrich T. Reichenberger P.O. Box 7707 Wichita, KS 67277 General Atomics Co. Attn D. I. Roberts P. O. Box 81608 San Diego, CA 92138

Gould Inc. Attn E. N. Aqua 540 E. 105 St. Cleveland, OH 44108

Gould Inc. Attn G. Davies 540 E. 105th St. Cleveland, OH 44108

Howmet Corporation Technical Center Attn L. Dardi 699 Benston Rd. Whitehall, MI 49461 Howmet Corporation Technical Center Attn J. VanderSluis 699 Benston Rd. Whitehall, MI 49461

Howmet Corporation
Turbine Components Div.
Attn Mr. Burd
Dover, NJ 07801

Howmet Corporation Turbine Components Div. Attn E. Carozza Mr. Burd Dover, NJ 07801

Huntington Alloys Div. International Nickel Co. Attn J. Cundiff Huntington, WV 25720

IIT Research Institute Attn M. A. Howes 10 West 35th Street Chicago, IL 60616

Intermetco Attn J. Siergiej 300 Concord Road Wayland, MA 01778 Jetshapes, Inc. Attn F. Jaeger Rockleigh Industrial Park Rockleigh, NJ 07647

Kelsey Hayes Co. Attn Wm. E. Good Heintz Div. Front St. and Olney Ave. Philadelphia, PA 19120 Thomas McNamara Consultant 42701 Main St., SP 154 San Jacinto CA 92383

METCO Inc. Attn V. Lanza 1101 Prospect Ave. Westbury, L.I., NY 11590 METCO Inc. Attn C. Lewis 3400 A Oak Cliff Rd. Atlanta, GA 30340

Rand Corp.
Attn J. Richard Nelson
Washington Research Div.
2100 M St.
Washington, DC 20037

Rocketdyne Division Attn J. Frandsen Rockwell International 6633 Canoga Ave. Canoga Park, CA 91304

Rockwell International Attn L.L. McHughes General Aviation Div. 5001 N. Rockwell Ave. Bethany, OK 73008 Special Metals, Inc. Attn J. Pridgeon Middle Settlement Road New Hartford New York 13413

Huntington Alloys Div. International Nickel Co. Attn R. Haeberle, Jr Huntington, WV 25720

Huntington Alloys Div. International Nickel Co. Attn F. Perry Huntington, WV 25720

IIT Research Institute Attn V. Hill 10 West 35th Street Chicago, IL 60616 IIT Research Institute Attn. R. Firestone 10 West 35th St. Chicago IL 60616

Kaman Sciences Corp. Attn D. H. Seitz P. O. Box 7463 Colorado Springs CO 80933

Kelsey Hayes Co. Attn W.G. Koby Heintz Div. Front St. and Olney Ave. Philadelphia, PA 19120

MCIC
Battelle Memorial Inst.
Attn H. Mindlin
Columbus, OH 43201

Martin Marietta Attn C.H. Lund 15 N. Windsor Rd. Arlington Hts IL 60004

Pacific Southwest Airlines Attn E. Chambers 7707 Consolidated Way San Diego, CA 92121 Pan American World Airways Attn W.B. Hibbs Pan Am Building New York, NY 10017

Rockwell International Attn V. Taylor General Aviation Div. 5001 N. Rockwell Ave. Bethany, OK 73008

Rockwell International Attn. E. Mathwig General Aviation Div. 5001 N. Rockwell Ave. Bethany, OK 73008

Cabot Corp. Attn D. Klarstrom 1020 W. Park Ave. Kokoma, IN 46901

Stellite Division Cabot Corporation Attn M. Rothman 1020 West Park Ave. Kokomo, IN 46901

Sundstrand Attn D. Augustine 4747 Harrison Ave Rockford, IL 61101 Swearingen Aviation Corp. Attn R. McKelvey P.O. Box 32486 San Antonio, TX 78284

TRW Inc. Attn C.S. Kortovich 23555 Euclid Ave. Cleveland, OH 44117

TRW Inc.
Attn J. McCarthy
23555 Euclid Ave.
Cleveland, OH 44117

TRW Inc. Attn T. Piwonka 23555 Euclid Ave. Cleveland, OH 44117

TRW Inc. Attn C. Vishnevsky 23555 Euclid Ave. Cleveland, OH 44117

Turbine Support Co.
Attn R. Van Cleaf
P. O. Box 20148
P.O. Box 20148
San Antonio, TX 78220

Union Carbide Corp.
Linde Division
Attn: E. B. Cook, Jr.
441 Sackett Pt. Rd.
North Haven, CT 06473

United Tech Rsch Center Attn B. Thomson East Hartford, CT 06108 United Tech Rsch Center Attn Library East Hartford, CT 06108

Universal Cyclops Attn R. Gasior Mayer Street Bridgville, PA 15017 Universal Cyclops Attn Wm. Kent Mayer St Bridgeville PA 15017

Vought Corp. Attn Library 2-50370/TL 7-67 P.O. Box 5907 Dallas TX 75222 Westinghouse R + D Center Attn D. Moon Beulah Rd. Pittsburgh, PA 15235

Teledyne Allvac Attn S. C. Pearman P. O. Box 759 Monroe, NC 28110

Teledyne Allvac
Attn R. Kennedy
Wm. Thomas
P. O. Box 759
Monroe, NC 28110

TRW Inc. Attn C. Barth 23555 Euclid Ave. Cleveland, OH 44117 TRW Inc. Attn D. Maxwell 23555 Euclid Ave. Cleveland, OH 44117

TRW Inc. Attn E. A. Steigerwald Metals Division Minerva, OH 44657 TRW Inc. Attn J. Preston Metals Division Minerva, OH 44657

United Airline Attn Y. Tekerian San Francisco Airport San Francisco CA 94128 United Airlines - SFOEG Attn J. K. Goodwine San Francisco Airport CA 94128

United Tech Rsch Center Attn F. D. Lemkey East Hartford, CT 06108

Universal Cyclops Attn L. Lherbier Mayer St. Bridgeville PA 15017

Vought Corp. Attn W.R. Boruff 2-53220 P.O. Box 5907 Dallas TX 75222 Vought Corp. Attn O.H. Cook 2-53400 P.O. Box 5907 Dallas TX 75222

Westinghouse Electric Co. Attn R. L. Ammon P.O. Box 10864 Pittsburgh, PA 15236 Westinghouse Electric Co. Attn D. Goldberg P.O. Box 10864 Pittsburgh, PA 15236

Westinghouse Electric Co.
Attn E. Crombie C-210
P.O. Box 251
Concordville, PA 19331

1. Report No.	2. Government Accession No.	3. Recipient's Catalog No.	
CR-174652			
4. Title and Subtitle	5. Report Date		
Low-Cost Single-Crystal Turb	April 1984		
Volume 2	6. Performing Organization Code		
7. Author(s)		8. Performing Organization Report No.	
T. E. Strangman R. E. Dennis B. R. Heath		Garrett 21-4314-2	
		10. Work Unit No.	
9. Performing Organization Name and Address			
Garrett Turbine Engine Compa A Division of The Garrett Co	11. Contract or Grant No.		
Phoenix, Arizona 85010	NAS3-20073		
		13. Type of Report and Period Covered	
12. Sponsoring Agency Name and Address National Aeronautics and Space Administration Washington, D.C. 20546		Project Completion Report Project 3	
		14. Sponsoring Agency Code	

15. Supplementary Notes

Project Manager:

Robert L. Dreshfield, Materials Division NASA-Lewis Research Center, Cleveland, Ohio

16. Abstract

The overall objectives of Project 3 were to develop the exothermic casting process to produce uncooled single-crystal (SC) HP turbine blades in MAR-M 247 and higher strength derivative alloys and to validate the materials process and components through extensive mechanical property testing, rig testing, and 200 hours of endurance engine testing.

These Program objectives were achieved. The exothermic casting process was successfully developed into a low-cost nonproprietary method for producing single-crystal castings.

Single-crystal MAR-M 247 and two derivative DS alloys developed during this project, NASAIR 100 and SC Alloy 3, were fully characterized through mechanical property testing. SC MAR-M 247 shows no significant improvement in strength over directionally solidified (DS) MAR-M 247, but the derivative alloys, NASAIR 100 and Alloy 3, show significant tensile and fatigue improvements.

Firtree testing, holography, and strain-gauge rig testing were used to determine the effects of the anisotropic characteristics of single-crystal materials. No undesirable characteristics were found. In general, the single-crystal material behaved similarly to DS MAR-M 247. Two complete engine sets of SC HP turbine blades were cast using the exothermic casting process and fully machined. These blades were successfully engine-tested.

17. Key Words (Suggested by Auth	or(s))	18. Distribution Sta	itement	
Turbine-Blade Single-Crystal Alloy-Selection Ni-base Alloys Investment Casting Exothermic-Heating	Columnar-Grain MAR-M 247 NASAIR 100 Alloy 3			
19. Security Classif. (of this report)	20. Security Class	sif. (of this page)	21. No. of Pages	22. Price*
Unclassified	Unclass	ified	61	